

# Rödtjära

## Classic Pine Tar Paint in a red color

### General

Rödtjära is a classic pigmented pine tar. It gives the surface a traditional Falun red appearance. Our Pine Tar Paint provides effective protection against water penetration and extends the lifespan of the wood. The strong tar scent fades after a few days and is barely noticeable after a month.

Auson Rödtjära contains various resins and terpenes. Resins are the tree's natural defense against microorganisms and help heal damage. Our pine tar is produced by heating resin-rich pine wood in a kiln. What makes our Tar Products unique is their high tar content—read more about this in our brochure at [www.Tjarfarg.se](http://www.Tjarfarg.se).

Rödtjära achieved the best results in Folksam's paint test in 2012, where mold and algae growth, cracking, and flaking were evaluated.

### Areas of Use

Rödtjära can be used on wood previously treated with distemper paint (e.g., Falun red paint) and iron vitriol, as well as on untreated or previously pine tar-treated wood such as facades, fences, wooden roofs, and other outdoor wooden structures.

### Instructions for Use

Read the safety data sheet and complete painting guide at: [www.Tjarfarg.se](http://www.Tjarfarg.se)

### Packaging

0,1 liter can  
0,9 liter can  
2,7 liter can  
9 liter can

### Technical Data

|                             |   |
|-----------------------------|---|
| Color:                      | Red (matte)   |
| Density:                    | 1,10 ± 0,03 kg/liter  |
| Solids content (by weight): | 82 % ± 3 %  |
| Coverage:                   | 5-8 m <sup>2</sup> /liter depending on the substrate  |
| Drying time:                | From a few days to several weeks depending on weather conditions, wood type, coating thickness, and how well the tar has penetrated the substrate |
| Thinner:                    | Gum turpentine or denatured alcohol (T-röd)   |
| Cleaning:                   | Gum turpentine or denatured alcohol (T-röd)   |

**For further information, see the safety data sheet or the instructions on the packaging.**

Edition: 2026-04/27 / HA